

TremPro® 626

Single Component General Purpose Textured Polyurethane Sealant

Product Description

TremPro 626 is a one-part, medium modulus, gun grade polyurethane sealant. It is designed for use in many applications, including lap joints and seams on trucks, containers, mobile homes, recreational vehicles, rail cars, etc.

The product has excellent adhesion to most substrates without the use of a primer. Once cured, the product exhibits tenacious adhesion and has the ability to be subjected to stress and vibration as well as expansion and contraction within a joint.

Basic Uses

Tremco 626 is a tough, elastomeric, polyurethane sealant designed for a variety of uses within the transportation industry. It is especially effective in holding roof sheets in place against normal load vibration and air forces.

It is a superior sealant for log home chinking, butt joints for pre-engineered metal buildings and applications that require continuous immersion in water.

Fasteners may be set through the uncured TremPro 626, which will act as a sealer.

Colors

Buff, Ivory, Dark Bronze, White, Gray, Black, Aluminum, Bronze, Redwood Tan, Stone and Limestone.

Packaging

10.1 oz. (300 ml) cartridges, 20 oz. (600 ml) sausages, 5-gallon (19 L) pails or 55-gallon (208 L) drums.

INSTALLATION

Surface Preparation

For good adhesion, the joint interface must be sound, clean and dry. Depending on the substrates, the joint surface may require a thorough wire brushing with a steel wool or Scotch Brite pad and/or solvent wipe.

Tooling & Cleaning

Tooling is recommended immediately after application to insure firm, intimate contact with the joint interface. Dry tooling is preferred. Excess sealant and smears adjacent to the joint can be removed with Xylol or Toluol before sealant cures.

Application

Cartridges of TremPro 626 are easy to apply with conventional caulking equipment.

Bulk units of TremPro 626 are easily pumped by equipment manufactured for that purpose.

Air pressure of 100 lbs. And pump ratios of 20:1 or 40:1 are typically used. Line sizes should be at least 1" if travel of 25 feet or more is necessary. Fill joint completely and tool.

Maintenance

Damaged sealant can be repaired. For repair procedures consult your TremPro sales representative or Tremco distributor.

Limitations

- Do not apply over damp or contaminated surfaces.
- For in-plant applications, ensure adequate ventilation at all times.
- Consult Tremco's MSDS for information regarding exposure limits and other important safety information. If vapor concentration may exceed applicable exposure limits, all exposed employees must wear suitable respiratory protection and other personal protection equipment in accordance with applicable OSHA requirements.
- TremPro 626 is not approved for construction applications in occupied structures, even if no occupants are present during product use.
- For log home chinking, TremPro 626 should be used for exterior applications only.

Warranty

Tremco warrants its sealants to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco sealants. Tremco's sole obligation shall be, at its option, to replace, or refund the purchase of the quantity of Tremco sealant proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

TYPICAL PHYSICAL PROPERTIES

Cure Rate	48 - 72 hours
Sag Resistance	Non-Sag in 1/2" Joint
Shore A Hardness	35 - 45
Tensile Strength	150 - 200 psi
Elongation	210 - 230 %
Stain and Color Change	None
Weight Loss, 24 Hours (Uncured)	Max. 10 % at 100°C
Peel Strength on Aluminum	15 - 20 pli

