



# WHITECOTE

## BRILLIANT WHITE COATING

### Supplementary Instructions

*Please Read Carefully Before Attempting to use WHITECOTE*

#### PRODUCT DESCRIPTION

**WHITECOTE** is a glossy, non-UV sensitive two-component white coating for application over primed metal and painted surfaces. **WHITECOTE** may be applied by brush or spray, and will cure to a rock-hard, non-porous finish that won't crack, chip, or peel. It is an excellent topcoat for **POR-15 Rust Preventive Paint**. **WHITECOTE** has unusually good hiding power when applied according to directions, and two coats should always be applied. **WHITECOTE** has excellent adhesion characteristics, is not sensitive to sunlight, and is highly chemical resistant. It will dry to the touch in two hours or less and should be topcoated two hours after the first coat is applied. **SPECIAL NOTE:** Although **WHITECOTE** will be dry to the touch in a few hours, **it will not reach maximum hardness until it has cured for at least 96 hours.**

Your **WHITECOTE** purchase includes two items. If you bought the quart size, you received a quart can which contains 24 ounces of **WHITECOTE** basic mix plus an 8 ounce can of **HARDENER/ACTIVATOR**. If you bought the gallon size, you received a gallon can which contains 96 ounces of **WHITECOTE** basic mix plus a quart can of **HARDENER/ACTIVATOR**.

**WARNING:** Your can of **HARDENER/ACTIVATOR** is filled to the very brim and is sealed with a screw-cap and a metal insert underneath. Remove the insert carefully. Cover with a paper towel while prying off to avoid accidental spillage or splash. Try to open your **HARDENER/ACTIVATOR** in a dry area because it is extremely moisture-sensitive, and prolonged exposure to moisture will shorten its life. Keep tightly capped while not in use. **FOR CLEANUP:** Use **POR-15 Solvent** or lacquer thinner. **TO THIN Whitecote,** use **Xylene (Xylol)**.

If you intend to use all of your quart or gallon at once, empty the entire **HARDENER/ACTIVATOR** can into the **WHITECOTE** paint can, stir for a few minutes, **then paint**. Do not shake as this will create air bubbles. **WHITECOTE** has a pot life of 2 - 3 hours, so mix what you need accordingly. **NOTE:** Your **WHITECOTE** basic mix is not moisture-sensitive before you add the **HARDENER/ACTIVATOR**, but after it is added, the blended mixture is **very** moisture-sensitive! **PARTIAL MIXES:** You may mix partial quantities of **WHITECOTE** for small jobs, and you may use any measuring device you happen to have around (coffee scoop, measuring spoons, measuring cups, etc. Simply use the following proportion:

**1 Part HARDENER/ACTIVATOR to 3 Parts WHITECOTE**

**Remember...** your **HARDENER/ACTIVATOR** **IS VERY MOISTURE-SENSITIVE** and should be kept tightly capped when not in use. Unused mixed **WHITECOTE** will begin to harden (cure) after about 3 hours and cannot be used again.