

		Elements					Comments
		Bal	Mn	Fe	Cu	Zn	
Sample	New 2024-T3 Stock	97.62%		0.31%	1.98%	0.09%	Slightly below spec Cu content due to alclad skew
	1955 Cali Built, all skins	94.34%	0.55%	0.29%	4.80%	0.29%	2024, stamped as 24 S T 3. Sampled from back side
	1961 Ohio Built, all skins	96.56%		0.46%	2.92%	0.06%	2024 with Slightly below spec Cu content due to alclad skew
	1963 Cali Built, all skins	98.97%		0.28%	0.15%	0.59%	5000 series with excess Zn? Not enough Cu to be a 2xxx series
	1963 Ohio Built, all skins	98.49%		0.36%	0.17%	0.57%	5000 series with excess Zn? Not enough Cu to be a 2xxx series
	1975 Ohio end cap	98.21%		0.43%	0.14%	0.58%	5000 series with excess Zn? Not enough Cu to be a 2xxx series
	1975 Ohio side	96.75%		0.40%	2.72%	0.11%	2024 with Slightly below spec Cu content due to alclad skew
	1991 Ohio Built, all skins	98.16%	1.03%	0.62%	0.13%	0.05%	3000 series, documents suggest 3005
	2005 Ohio Built, all skins	98.28%	0.99%	0.64%	0.08%	0.01%	3000 series?